

## ŻELIWO SFEROIDALNE

<i>Gatunek wg norm</i>					
<b>PN-EN 1563:2000</b>	<b>PN-92/H-83123</b>	<b>DIN EN 1563:1997</b>	<b>DIN 1693</b>	<b>ASTM A536-84</b>	<b>GOST 7293-85</b>
EN-GJS 350-22	350-22	EN-GJS 350-22	-	-	Vc 35
EN-GJS 400-15	400-15	EN-GJS 400-15	GGG-40 (0.7040)	60-40-18	Vc 45-12
EN-GJS 400-18	400-18	EN-GJS 400-18	-	60-40-18	Vc 40
EN-GJS 450-10	450-10	EN-GJS 450-10	-	~65-45-12	Vc 45
EN-GJS 500-7	500-7	EN-GJS 500-7	GGG-50 (0.7050)	65-45-12	Vc 50-7
EN-GJS 600-3	600-3	EN-GJS 600-3	GGG-60 (0.7060)	80-55-06	~Vc 60-2
EN-GJS 700-2	700-2	EN-GJS 700-2	GGG-70 (0.7070)	100-70-03	Vc 70-2
EN-GJS 800-2	800-2	EN-GJS 800-2	GGG-80 (0.7080)	120-90-02	Vc 80-2
EN-GJS 900-2	900-2	EN-GJS 900-2	-	120-90-02	-